

MARIPOOL®

Protective Coating for
Swimming Pools,
UV-stable,
Non-Chalking

TECHNICAL DATA SHEET
Date: 19.12.2022 – Version 22

Product Description

MARIPOOL® is a colored, chemical resistant, abrasion resistant, thin-layer protective pool coating. MARIPOOL® is UV-stable and resistant to usual pool chemicals. The MARIPOOL® is weather-stable so it can be applied also on exterior pools.

1

Product Information

- One-component, solvent based,
- Moisture-cured cold applied and cold curing aliphatic synthetic polymer

Packaging

- 1/5/10/20 kg metal pails

Color

- White, Beige, Dark Blue and Light Blue
- Other RAL colors supplied on request

Shelf Life

- 9 months from date of production

Storage Conditions

- Pails should be stored in dry and cool rooms. Protect the material against moisture and direct sunlight. Storage temperature: 5°-35°C. Products should remain in their original, unopened containers, bearing the manufacturers name, product designation, batch number and application precaution labels.

Advantages

- Simple application (roller or airless spray)
- Resistant to abrasion
- Colour stable
- Resistant to pool chemicals
- No water absorption, when applied
- Gives a satin and easy-to-clean surface
- No chalking effect
- Resistant to frost

■ Uses

MARIPOOL® is used on concrete, cementitious mortar, sand-cement screeds etc, on exterior or interior surfaces.

MARIPOOL® is used for protection in:

- Swimming Pools
- Fountains
- Ponds
- Water Tanks
- Water Channels, etc

■ Consumption

0,150 kg/m² per layer, applied in 3 layers

This coverage is based on practical application by roller onto a smooth surface in optimum conditions. Factors like surface porosity, temperature, humidity, application method and finish required can alter consumption.

■ Certifications



EN1504-2: Surface protection for concrete. (0.45kg/m²)



Technical Data

PROPERTY	RESULTS	TEST METHOD
Hardness (SHORE A Scale)	>80	ASTM D 2240
UV and Colour stability	Excellent	
Resistance to Water Pressure	No Leak (1m water column, 24h)	DIN EN 1928
Surface chalking after 2000h of accelerated aging (DIN EN ISO 4892-3, 400 MJ/m²)	No chalking observed. Chalking grade 0	DIN EN ISO 4628-6
Water Vapor Permeability (0.45kg/m²)	2.15 gr/m ² /day	ISO 7783
Carbon Dioxide Permeability (0.45kg/m²)	0.31 gr/m ² /day	EN 1062-6
Water Permeability (0.45kg/m²)	1.78 gr/m ² /day	EN 1062-3
Adhesion to concrete	2.0 N/mm ² (concrete surface failure)	EN 1542
UV accelerated ageing, in the presence of moisture	Passed - No significant changes	EOTA TR-010
Hydrolysis (5% KOH, 7days cycle)	No significant elastomeric change	Inhouse Lab
Service Temperature	-40°C to +90°C	Inhouse Lab
Tack Free Time	1-3 hours	Conditions: 20°C, 50% RH
Light Pedestrian Traffic Time	24 hours	Conditions: 20°C, 50% RH
Final Curing time	7 days	Conditions: 20°C, 50% RH
Chemical Properties	Good resistance against acidic and alkali solutions (5%), detergents, seawater and oils.	

■ Application

Surface Preparation

Careful surface preparation is essential for optimum finish and durability. The surface needs to be clean, dry and sound, free of any contamination, which may harmfully affect the adhesion of the coating. Maximum moisture content should not exceed 5%. New concrete structures need to dry for at least 28 days. Old coatings, dirt, fats, oils, organic substances and dust need to be removed by a grinding machine. Possible surface irregularities need to be smoothed. Any loose surface pieces and grinding dust need to be thoroughly removed.

WARNING: Do not wash surface with water!

WARNING: Do not apply coating directly on highly elastic cementitious waterproofing membranes. Do not apply coating on polymer based membranes or old coatings, only on low flexibility cementitious screeds, cement mortar, concrete, etc. Do not apply the coating on top of primers but directly on cement

Repair of cracks:

Clean cracks and hairline cracks, of dust, residue or other contamination. Fill all cracks with suitable putty. The next day smoothen the putty surface with a sandpaper or a mechanical grinder.

COATING

Stir well before using. For best results, the temperature during application and cure should be between 5°C and 35°C. Low temperature retards cure while high temperature speeds up curing. High humidity may affect the final finish. Apply the first layer, of coloured MARIPOOL® coating.

After 1-3 hours (not later than 4 hours) apply the second layer, of MARIPOOL® coating.

Once again allow 1-3 hours for the coating to cure (not more than 4 hours), then apply the third layer of MARIPOOL®.

ATTENTION: Protect material against tanning agents and sunblock oils, as discolouration could occur. In case of electrolysis water treatment, discolouration could occur.

■ Safety measures

MARIPOOL® contains solvents. See information supplied by the manufacturer. Flammable. Use only at places with adequate ventilation. Please study the Safety Data Sheet. **PROFESSIONAL USE ONLY**

Our technical advice for use, whether verbal or written, is given in good faith and reflect the current level of knowledge and experience with our products. When using our products, a detailed object-related and qualified inspection is required in each individual case in order to determine whether the product and /or application technology in question meets the specific requirements and purposes. We may guarantee only that our products are compliant with their technical specification; correct application of our products therefore falls entirely within your scope of liability and Users are responsible, in any case, for complying with local legislation and for obtaining any required approvals or authorizations, when necessary, either for their purchase and/or for their use. Values in this technical data sheet are given as examples and may not be regarded as specifications. For product specifications contact our Technical department. The new edition of the technical data sheet supersedes the previous technical information and renders it invalid. It is therefore necessary that you always have to hand the current code of practice.

* All values represent typical values and are not part of the product specification